

# addastone<sup>®</sup>

Resin Bonded Aggregate Surfacing

ALL BASE DETAILS ARE INTENDED AS A GUIDE ONLY  
AND DO NOT CONSTITUTE A SPECIFICATION



**Addastone Surface Course**  
Resin bonded, hand scattered aggregate finish by Addagrip approved installers.

**Addacryl Sealer**  
To fill surface voids only

**Macadam Surface Course**  
Laid by others in well compacted layers to a minimum fall of 1%

**Base and sub-base** requirements will vary depending on the individual project's requirements, loadings etc

AC10 Open SURF 100/150 QF  
proprietary ref 7.2 or 30mm of  
10mm SMA (max 125 pen)

*Newly laid surfaces should be treated 7 days or longer after installation to allow any volatile oils in the surface to oxidize. If areas need to be installed sooner please liaise with your approved Addastone Installer.*

or



**Addastone Surface Course**  
Resin bonded, hand scattered aggregate finish by Addagrip approved installers.

**EP Addastone Primer**  
where required

**Concrete Alternative**

Apply quartz grit into uncured primer

Concrete slab, laid to take expected loads, laid in bays not exceeding 20m with a maximum bay length of 6m, on to a suitable granular sub-base Type 1 to DTLR 'Specification for Highway Works' to clause 803. Allow a minimum of 28 days to cure before applying Addastone, alternatively, install Tarmac Toproc Microsilica Concrete, reducing cure time to approximately 7 days. Further details are available on request. Refer to the Addastone data sheet for surface preparation information.

**NOTE:** A suitable steel, wood, brick, stone or aluminium edging should be provided to ensure a neat edge detail. Any advice, recommendation or information given by Addagrip Surface Treatments UK Limited is based on practical experience and is believed to be accurate at the time of publication, no liability or responsibility of any kind (including liability for negligence) is accepted in this respect by the company, its Servants or Agents. The figures quoted do not constitute a specification, they represent typical values obtained for this product.