

# addaset<sup>®</sup>

Resin Bound Aggregate Surfacing

## Car Parks and Access Road

Typical base build up for cars & occasional delivery vehicles

0.5mm dia grit cast onto uncured surface

### Surface Course

Hand applied and trowelled to a smooth finish by Addagrip approved installers.



The typical depth of Addaset resin bound paving surface.

3mm aggregate formulation requires a minimum of 16mm

6mm aggregate formulation requires a minimum of 18mm

10mm aggregate formulation requires a minimum of 24mm

### Binder Course

Laid by others in well compacted layer to a minimum fall of 1.5%.



A 35mm depth of AC 14 close surf asphalt concrete max 100/150 pen to BS EN 13108-1:2006. (Bituminous Macadam).

### Road Base

laid by others in well compacted layer to a minimum fall of 1.5%.



A 70mm depth of AC 32 dense base asphalt concrete max 100/150 pen to BS EN 13108-1:2006. (Bituminous Macadam)

### Sub-base

laid by others in well compacted layers to a minimum fall of 1.5%.



A 200-350mm depth of well-compacted non-frost susceptible Type 1 granular sub base to SHW clause 803 or locally available secondary or recycled aggregates which comply with the requirements of the SHW works for sub-bases.

Terram 900/1000/Advantage geotextile membrane to prevent upward migration of fine soil particles (optional).

### Capping Layer

if required



### Sub-grade



**NOTE:** A suitable steel, wood, brick, stone or aluminium edging should be provided to ensure a neat edge detail.

Any advice, recommendation or information given by Addagrip Surface Treatments UK Limited is based on practical experience and is believed to be accurate at the time of publication, no liability or responsibility of any kind (including liability for negligence) is accepted in this respect by the company, its Servants, or Agents. The figures quoted do not constitute a specification, they represent typical values obtained for this product.

